



M60200

# **HIGH DENSITY POLYETHYLENE**

## INJECTION MOULDING GRADE

M60200 is a High Density Polyethylene (HDPE) grade designed for injection moulding applications. M 60200 is suitable for moulding of houseware and commodities. Due to narrow molecular weight distribution of resin, articles exhibit excellent gloss. The resin also imparts good rigidity, stiffness, impact resistance coupled with good melt flow properties required for mould filling of large articles.

Typical Characteristics*			
Property	Test Method	Unit	Typical Value**
Density (23°C)	ASTM D1505	g/cc	0.958
MFI (190°C/2.16 kg)	ASTM D1238	g/10 min	20.0
Tensile Strength at Yield	ASTM D638	MPa	25
Elongation at Yield	ASTM D638	%	10
Flexural Modulus	ASTM D790	MPa	900
Hardness	ASTM D2240	Shore D	69
Vicat Softening Point	ASTM D1525	°C	126

<sup>\*</sup>Typical Characteristics and not to be taken as specifications

#### **Applications**

Houseware, Storage bins.

### **Regulatory Information**

• Meets the requirements stipulated in standard IS: 10146 on "Specification for Polyethylene for safe use in contact with foodstuffs, pharmaceuticals, and drinking water". It also conforms to the positive list of constituents as prescribed in IS: 10141. The grade and the additives incorporated in it also comply with the FDA:CFR Title 21,177.1520, Olefin polymers.

#### **Storage Recommendations**

• Bags should be stored in dry/closed conditions at temperatures below 50°C and protected from UV/direct sunlight.

Reliance Industries Limited, Product and Application Technology Group.

Swastik Mill Compound, V. N. Purav Marg, Chembur, Mumbai-400 071. Tel.: +91-22-6767 7000. E-mail: polymer\_patsupport@ril.com Website: www.ril.com

<sup>\*\*</sup>Mechanical Properties are on Injection Moulded Specimen

<sup>•</sup> The information and data presented herein is true and accurate to the best of our knowledge. No warranty or guarantee expressed or implied, is made regarding performance or other wise. This information and data may not be considered as a suggestion to use our products without taking into account existing patents, or legal provisions or regulations, whether national or international. • The user of any information and/or data is advised to obtain the latest details from any of the offices of the company or its authorised agents, as the information and/or data is subject to change based on the research and development work undertaken by the company.