



CI20MN

IMPACT COPOLYMER

FOR INJECTION MOULDED PRODUCTS

Repol C120MN is recommended for use in **Injection Moulding** processes where good impact-stiffness balance is required. It is an ideal material to use in pails, luggage shells, industrial and automotive components. Repol C120MN contains antistatic agents that reduces static charge build-up in products.

Typical Characteristics			
Property	Test Method	Unit	Typical Value*
Melt Flow Rate (230°C/2.16 kg)	ASTM D1238	g/10 min	12
Tensile Strength at Yield (50 mm/min)	ASTM D638	MPa	24
Elongation at Yield (50 mm/min)	ASTM D638	%	7
Flexural Modulus (1% secant)	ASTM D790A	MPa	1050
Notched Izod Impact Strength (23°C)	ASTM D256	J/m	150
Heat Deflection Temperature (455 kPa)	ASTM D648	°C	105

^{*} Typical values, not to be taken as specification. All the mechanical properties as per ASTM D638 Type I specimen injection moulded in accordance with ASTM D4101

Applications

Paint pails, luggage, industrial components.

Regulatory Information

 Meets the requirements stipulated in IS 10910 on 'Specification for Polypropylene and its Copolymers for safe use in contact with foodstuff, pharmaceuticals, and drinking water'. Additives incorporated in this grade conform to the positive list of constituents as prescribed in IS 10909. The grade and the additives incorporated in it also comply with the FDA:CFR Title 21,177.1520, Olefin polymers.

Storage Recommendations

 $\bullet \ \ Bags \ should be stored in \ dry/closed \ conditions \ at \ temperatures \ below \ 50^{\circ}C \ and \ protected \ from \ UV/direct \ sunlight \ below \ 50^{\circ}C \ and \ protected \ from \ UV/direct \ sunlight \ below \ 50^{\circ}C \ and \ protected \ from \ UV/direct \ sunlight \ below \ 50^{\circ}C \ and \ protected \ from \ UV/direct \ sunlight \ below \ 50^{\circ}C \ and \ protected \ from \ UV/direct \ sunlight \ below \ 50^{\circ}C \ and \ protected \ from \ UV/direct \ sunlight \ below \ 50^{\circ}C \ and \ protected \ from \ UV/direct \ sunlight \ below \ 50^{\circ}C \ and \ protected \ from \ UV/direct \ sunlight \ below \ 50^{\circ}C \ and \ protected \ from \ UV/direct \ sunlight \ below \ 50^{\circ}C \ and \ protected \ from \ UV/direct \ sunlight \ below \ 50^{\circ}C \ and \ protected \ from \ below \ from \ below \ 50^{\circ}C \ and \ protected \ from$

Reliance Industries Limited, Product - Application & Technology Group, PRTC,
Swastk Mill Compound, V. N. Purav Marg, Chembur, Mumbai-400 071. Tel.: +91-22-6767 7000. E-mail: polymer_patsupport@ril.com Website: www.ril.com